

Traceable Certificate Number: 3169168A
Contractor: ADVANCED SCALE INC
 13 DELTA DR UNIT 6
 LONDONDERRY, NH 03053-2372

Purchase Order Number: 9494
Client: ADVANCED SCALE INC
 13 DELTA DR UNIT 6
 LONDONDERRY, NH 03053-2372

Date Received: 22 Feb 2021
Date Calibrated: 25 Feb 2021 to 26 Feb 2021
Recalibration Date: 25 Feb 2022
NIST Certificate Number: 684/291344-18 & 684/292805-19

If there are two NIST numbers, one or both may apply

Calibrated By: 03, 17
Procedure: WI05-0095 Rev. D
Condition of Weights: Acceptable for Calibration
Description of Weights: 5 mg to 100 g Polished Weight Kit, ASTM Class 1, Set S/N 0M31
Comments:



Key Notes

- Finish Indicates the weight does not meet the finish requirements
- Material Indicates the weight does not meet the material requirements
- New Wt Indicates new weight
- Missing Wt Indicates replaced missing weight with new weight
- Damaged Wt Indicates replaced damaged weight
- Replaced OOT Indicates replaced out of tolerance weight
- OOT Indicates correction plus or minus Uncertainty greater than or equal to MPE
- Magnetic Wt Indicates replaced magnetic weight
- Design Indicates the weight does not meet the design or shape requirements
- Repainted Indicates the weight was repainted after As Found obtained
- Other See comments above

Cleaning Levels

- A Dusted with brush or cloth
- B Spot cleaned with ethyl alcohol
- C Full surface cleaned with ethyl alcohol
- D Spot cleaned with non-alcohol solvent followed by ethyl alcohol
- E Full surface cleaned with non-alcohol solvent followed by ethyl alcohol
- F No cleaning performed

Material Abbreviations

AL	Aluminum	TA	Tantalum
SS	Stainless Steel	BR	Brass
CI	Cast Iron	PL	Platinum
IR	Iron	NS	Nickel Silver
MS	Mild Steel	OR	Other/Unknown

Check with your local state agency for certification of compliance on Legal-for-Trade items. The weight accuracy class is referenced in the Description of Weights. Unless otherwise noted, the weights calibrated meet the requirements of the accuracy class. Results relate only to weights calibrated. The Surface Finishes of weights are evaluated visually. Weights are screened for magnetism using work instruction WI05-0035 when they are new, when requested by the customer or when weights are suspected of not meeting specifications. Density if measured is measured using OIML R111-1 (2004) method A2. Conventional Mass is reported based on a reference density of 8.0 g/cm³. The Uncertainty of Measurement is included in the determination of Maximum Permissible Error (MPE) Pass/Fail Criteria. The specifications for Maximum Permissible Error (MPE) can be found in NIST Handbook 105-1 (2019), NIST Handbook 105-1 (1990), ASTM E617-18 or OIML R111-1 (2004), manufacturer specifications or customer specifications.

The Uncertainty assigned to the Conventional Mass values are the result of the root-sum-square of the type A and type B components, calculated in accordance with NIST SOP 29 and the Guide to the expression of uncertainty in measurement, with coverage factor (k=2), to express the expanded uncertainty with an approximate 95.45% confidence level. This report is not to be used to claim product certification, approval, or endorsement by NVLAP, NIST, A2LA, or any government agency. This document shall not be reproduced, except in full, without the written approval of Rice Lake Weighing Systems.

Dan Demers, Metrologist

26 Feb 2021

Date:



Prepared By:
Rice Lake Weighing Systems® • PN 64784 • 06/20
 230 West Coleman Street • Rice Lake, WI 54868 • USA
 TEL: 715-234-9171 • FAX: 715-234-6967
 Definitions: <http://certs.ricelake.com/certs/DefinitionsV2.docx>
 Page 1 of 2



Certificate of Weight Calibration

ISO/IEC 17025 & ANSI/NCSL-Z540-1-1994 ACCREDITED

Traceable Certificate Number: 3169168A
 Client: ADVANCED SCALE INC
 Date Calibrated: 25 Feb 2021 to 26 Feb 2021

Temperature Range: 21.41 °C to 21.55 °C
 Pressure Range: 728.91 mmHg to 737.69 mmHg
 Relative Humidity Range: 49 % to 53 %

As Left Data (As Found only shown when different than As Left)

Nominal Value	Unique ID	True Mass	True Mass Corr. (mg)	Conv. Mass	Conv. Mass Corr. (mg)	(k=2) Unc. (± mg)	MPE (± mg)	MPE Pass	Assumed Density (g/cm ³)	Assumed Material	Const. Type	Balance Used	Reference Standard Set Used	Air Density (mg/cm ³)	Clean Level
5 mg	0M31	5.00310	0.00310	5.00310	0.00310	0.00095	0.010	Y	7.95	SS	I	503Q	L595Q	1.1438	A
20 mg	0M31	20.00022	0.00022	20.00020	0.00020	0.00090	0.010	Y	7.95	SS	I	503Q	L595Q	1.1439	A
200 mg	0M31	200.0005	0.0005	200.0004	0.0004	0.0011	0.010	Y	7.95	SS	I	503Q	L595Q	1.1436	A
200 mg	0M31.	199.9980	-0.0020	199.9978	-0.0022	0.0011	0.010	Y	7.95	SS	I	503Q	L595Q	1.1438	A
500 mg	0M31	499.9980	-0.0020	499.9976	-0.0024	0.0015	0.010	Y	7.95	SS	I	503Q	L595Q	1.1435	A
1 g	0M31	1.0000119	0.0119	1.0000110	0.0110	0.0018	0.034	Y	7.95	SS	I	503Q	L595Q	1.1442	A
2 g	0M31	2.0000041	0.0041	2.0000022	0.0022	0.0023	0.034	Y	7.95	SS	II	503Q	L595Q	1.1440	A
2 g	0M31.	2.0000162	0.0162	2.0000143	0.0143	0.0023	0.034	Y	7.95	SS	II	503Q	L595Q	1.1441	A
5 g	0M31	4.9999815	-0.0185	4.9999768	-0.0232	0.0041	0.034	Y	7.95	SS	II	503Q	L595Q	1.1437	A
10 g	0M31	10.0000351	0.0351	10.0000256	0.0256	0.0063	0.050	Y	7.95	SS	II	1958Q	L595Q	1.1575	A
20 g	0M31	20.0000313	0.0313	20.0000124	0.0124	0.0065	0.074	Y	7.95	SS	II	1958Q	L595Q	1.1576	A
20 g	0M31.	20.0000210	0.0210	20.0000022	0.0022	0.0065	0.074	Y	7.95	SS	II	1958Q	L595Q	1.1573	A
50 g	0M31	49.999974	-0.026	49.999927	-0.073	0.013	0.12	Y	7.95	SS	II	1958Q	L595Q	1.1575	A
100 g	0M31	100.000032	0.032	99.999938	-0.062	0.022	0.25	Y	7.95	SS	II	1958Q	L595Q	1.1571	A